

KLEIBERIT 658.9.90

Additive

Field of application

- Anti-scratch additive for self-mixing into UV-topcoat KLEIBERIT 659.9.02

Properties

Base:	Additive concentrate based on UV-curing acrylates
Consistency:	fluid
Colour:	colourless
Specific weight (20 °):	approx. 1.499 g/cm ³
Solid content:	approx. 99 %
Recommended dosage:	3,5 kg KLEIBERIT 658.9.90 per 20 kg KLEIBERIT 659.9.02
Identification:	Identification required according to EU regulations (see our safety data sheet).

Processing

Processing temperature: >22 °C

The KLEIBERIT 658.9.90 is to be stirred in thoroughly and completely in the KLEIBERIT 658.9.90.

High stirring speeds and shear forces are to be avoided in order to minimize building up of bubbles and foam.

The produced mixture of KLEIBERIT 658.9.90 and KLEIBERIT 659.9.02 should be used immediately after mixing.

If processed on the following day the mixture has to be stirred again.

Cleaning

Application tools and machine parts should be cleaned immediately with cleaner KLEIBERIT 816.0

Packaging

KLEIBERIT 658.9.90

Can, 3.5 kg net

Cleaner

KLEIBERIT 816.0

Metal canister, 4.5 kg net

Metal can, 23 kg net

Additional packaging sizes available upon request.

Storage

KLEIBERIT 658.9.90 can be stored in factory sealed containers for about 6 months.

Protect from heat and direct sunlight.

Version gt 07/10/2019; replaces previous versions

KLEIBERIT 658.9.90

Adhesive and Waste disposal

See our safety datasheet

Our containers are made of recyclable material. Well drained containers can be recycled.

Service

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.